



GLASSGO PAINTS

GLASSGO 2K ENAMEL DATA SHEET

Name : GLASSGO ENAMEL

Code : 2KMAN

Date Issued : 2018/01/06

SECTION 1. MANUFACTURER

Paintworx Manufacturing (Pty)Ltd
Registration No. 2005/005928/07

SECTION 2. DESCRIPTION

Product Name : 2K ENAMEL Code: 2KMAN Date Issued : 2018/01/06

SECTION 3. PRODUCT BENEFITS

Good adhesion.
Good general durability.
Good strength.
Resistant to oil spills & splashes and certain chemicals (petrol and diesel)

SECTION 4. PREPERATION

Use Glasso MS Primer as a first coat

SECTION 5. TECHNICAL DATA

Type : Hydroxy
Gloss Level : High Gloss
Re Coating Time : Within 24 hours
Viscosity : 75 – 85 KU
Practical Spread Rate : 4-6 sqm/1litre
Specific Gravity : 1.1 depending on colour (± 1.2 FOR WHITE)
Solid by volume : Base 42.83 / Mixed 2:1 32.10
Solid by Mass : Base 54.8 / Mixed 2:1 42.88
Drying Time : Surface 15 – 20 minutes
Hard 24 hours
Recommended DFT : ± 50 Microns 2-3 Coats

SECTION 6 . COLOUR RANGE

All Colours

SECTION 7. METHODS OF APPLICATION

Spray

SECTION 8. THINNING

2:1 Glassgo hardener & 2K Thinners

SECTION 9. CLEAN UP

2k Thinners

SECTION 10. PRECAUTION

USE IN WELL VENTILATED AREAS
HIGHLY FLAMMABLE
GOGGLES AND RESPIRATORS TO BE WORN IN CONFINDED AREAS
AVOID SKIN CONTACT

SECTION 11. PACKAGING

1 Litre
5 Litres
25 Litres
200 Litres

SECTION 12. FLASHPOINT

21 Degrees Celsius