TECHNICAL DATA SHEET

JOINTFINISHER PASTA

READY-TO-USE FINISHING COMPOUND





Product description

BAUTEC JOINTFINISHER PASTA consists of calcium carbonate, fillers, additives and a binder. It is a finishing and filling compound, type 3A in accordance with EN 13963. Article No.: 277965.

Areas of application

Multipurpose finishing compound for joint finishing (F2a), full-surface skim coating (finish levels F2a to F3), and smoothing various substrates. Suitable for indoor use on gypsum plasterboard and gypsum fibreboard, concrete and aerated concrete, plaster/render and masonry built with flat, adhesively bonded blocks.

Properties and benefits

• Ready to use	• No mixing or maturation time
• Smooth, creamy consistency	• Easy to apply
• Application with suitable F2a finishing tools	• Very easy to sand
• Finish levels F2a–F3	• Good adhesion

Storage, packaging and quality

Protect from frost, high temperatures and direct sunlight. At room temperature, product quality remains stable for at least 12 months. Packaging: 20 kg bucket. In accordance with EN 13963, the product undergoes initial testing and continuous production control and bears the CE marking.

APPLICATION

Application and recommendations

Substrate preparation

The substrate must be dry, load-bearing, stable, level and clean. Remove release agents and residues such as starch-based adhesive or wallpaper. Plasterboards must be securely fixed to a supporting frame; joints must be dry, clean and dust-free. Fill large cavities with a powder-based joint filler. Pre-filled joints must be completely dry and flush with the board surface.

Mixing and preparation

Stir the material and, if necessary, dilute with a little water. Use clean containers and tools, including a filling knife or another tool suitable for the F2a finish level.

Drying time and application temperature

The material hardens as it dries; drying time depends on air humidity and ambient temperature. During application and until completely dry, the temperatures of the material, substrate and surrounding air must not fall below +10 °C.

Application advice

Do not mix JOINTFINISHER PASTA with other materials. Clean equipment and tools with water immediately after use. Allow longer drying times for thicker layers, depending on the temperature and humidity.

Coatings and finishes

Always prime plasterboard with a suitable primer before applying finishes or coverings (such as wallpaper). Use only methylcellulose-based wallpaper adhesive. After hanging wallpaper or glass-fibre coverings, or applying synthetic-resin-based or cellulose-based plaster, provide adequate ventilation to ensure rapid drying.

Indicative consumption on plasterboard

Finish level	Consumption
F2a — joint finishing	Approx. 0.1 kg/m²
F2b over F2a	Approx. 0.5 kg/m²
F3 — full-surface skim coat, per mm thickness	Approx. 1.6 kg/m²

Exact consumption can only be determined by testing on the substrate concerned.