

ShaliPlast[®] PCE 200



High Performance Poly-Carboxylated Ether Based Superplasticiser

STP Limited

Description

ShaliPlast PCE[®] 200 is a third generation Poly-Carboxylated Ether based super-plasticizer for lower and medium grade concrete and mortar. It is an additive for concrete, mortar and plasters. It conforms to IS 9103 – 1999 and ASTM – C494 Type G. It also complies with IS : 2645 : 2003 as an integral waterproofing compound.

Characteristics

Colour	Light Brownish	Specific Gravity, 30 °C	1.05 ± 0.04
pH	6 - 8	Chloride Content	Nil
Dosages, by weight of cementitious material, %		0.5– 2.0	

Application

ShaliPlast[®] PCE 200 is especially suitable for the production of concrete mixes which require high early strength development, high water reduction and excellent flow-ability.

- For ready mix concrete.
- High workability concrete.
- Precast concrete.
- Fast track concrete.
- In situ concrete requiring fast stripping time.

Advantages

- Pronounced increase in the early strength development, resulting in very economical stripping times for precast and in situ concrete.
- Extremely high water reduction, resulting in high density, high strength and reduced permeability for water etc.
- Excellent plasticizing effect, resulting in improved flow-ability, placing and compacting behavior.
- Higher cohesion reducing risk of segregation and bleeding.
- Improved shrinkage and creep behavior.
- Free from chlorides or other ingredients promoting corrosion of steel reinforcement. It is therefore suitable for reinforced and pre-stressed steel.
- It is compatible with all types of Portland Cement including SRC (Sulphate Resistance Cement) and Cement Fillers / substitutes like PFA, GGBFS and Micro Silica. Always conduct trials before combining products in specific mixes and contact our Technical Service Department for information about specific combinations.

Application Methodology

- Add **ShaliPlast[®] PCE 200** to the dosing water or added with it in to the concrete mixer. It should not come into contact with dry cement.
- **Dosing:** Charge all concrete material in the proper order into the mixer with about 85% of the mixing water and mix for appropriate time. Add rest quantity of water with admixture to obtain the required slump and mix for additional 2 - 3 minutes.
- Overdosage may cause delay in setting time of concrete.
- **Formwork:** Forms for walls or narrow sections must be watertight, strong and must have good bracing. During the “Flowing period” the concrete will exert a higher pressure at the base of the form than conventional concrete. Form work for slabs is the same as for conventional concrete.

Health & Safety

- Avoid contact with skin / eyes and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 250 kg barrel.

Storage

Keep in cool and dry place, under shed, away from heat.

Shelf Life

12 months in original unopened condition.



STP Limited
Enhancing Structures' Life

Product Range

- Waterproofing and Insulation ■ Road Surfacing
- Sealants and Additives ■ Pipeline Coating
- Protective / Anti-Corrosive Coating ■ Epoxy Flooring
- Grouts / Admixtures ■ RestoFix- Repair / Rehabilitation
- Other Construction Chemicals



Advisory Cell: +91 81302 81114