# ShaliPatch® EC 20





## **Description**

**ShaliPatch® EC 20** (formerly known as ShaliPatch EC) is a three-component, cold applied, polymerized elastomeric concrete with excellent adhesion to substrate for

- crack filling ranging between 5 50 mm wide in concrete / flexible roads, and
- surface correction in concrete road / pavement.

**ShaliPatch® EC 20** is self-leveling, easily trowel-able into cracks and spall. It prevents percolation of water and other chemicals thus protecting it from wearing off.

## **Characteristics - Physical**

Colour	Black / Grey	Mixed density	1.80 ± 0.05
Drying Time, Touch, minutes	60	Application temperature, °C	5 to 45
Pot Life @ 30°C, minutes	10 ± 1	Chemical Resistance	Excellent
Solid % by volume	100	Curing Time	
Open to traffic time, hrs. minimum	2	Curing Time  Over coat, hrs.	2
Mixing ratio, by wt., A:B:C	3.6:0.9:5.5	Full cure, days	3

#### **Characteristics - Technical**

Property	Method	Result
Elongation after 7 days %, min	ASTM D 412	$30 \pm 2$
Compression, MPa  • 4 hrs.	ASTM D 695	3
1 day     INFRA PRIVA		5
Stress @ 5% deflection, 4 hrs., MPa	ASTM D 695	2
Tensile strength, 7 days, MPa	ASTM D 412	1.3 ± 0.07
Hardness, Shore D	ASTM D 2240	47 ± 3
Impact, -15°C, 1 lb., 10 ft	ASTM D 3029	No Cracking

## **Application**

- Excellent patching material for cracks and spalls on
  - Airport runways / Apron / Taxiways
  - PQC Roads / Bridges
  - Parking decks
  - Industrial floors
- · Easy to use solution in retrofitting airport runways with lighting.

#### **Advantages**

- High-load bearing capacity.
- Outstanding anti-spalling properties.
- Tough, Flexible and Durable.
- Rapid Cure time.
- Excellent resistance to chemical, saltwater, oil, acids, alkalies, crude oil, fuels and minerals.
- Compatible with both coal tar and asphalt emulsion-based sealers.
- Compatible with both concrete and bituminous pavement.
- Excellent to repair surface defects of the road.

## **Application Methodology**

## Surface Preparation

- Remove all loose gravel, dirt, oil, grease and foreign matter by jet of dry air.
- Ensure that.
  - The surface is structurally sound and dry.
  - In case of new concrete road, concrete is at least 28 days old.
  - Ambient temperature is not less than 5°C and not more than 35°C at the time ofapplication.
  - There is no standing water in the area to be repaired or in the area of application.
  - Mechanically grinding the surface is acceptable only when sand blasting is notpossible.
- Saw cut area to be repaired in geometrical shape.

#### Material Preparation

- Stir Component A thoroughly for uniformity.
- Mix component A (Resin) & component C (Aggregate) thoroughly by using speed drillmixer with a spiral type blade at the bottom of stirrer rod till homogeneous mix is obtained.
- Then add component B (Hardener) slowly, ensuring complete dispersion. Mix for a minimum of 2 3 minutes.

## Application of Material

- In case of concrete surface, prime the surface with ShaliPrime<sup>®</sup> PUM / ShaliPrime<sup>®</sup> 2E SF.
- Allow it to surface dry.
- Pour mixed material in to the cracks, finish surface with trowel, if required.
- Allow it to dry at least two hours before opening traffic. Curing time will vary according toweather conditions.
- Do not install ShaliPatch® EC 20 when any moisture is present or pavement temperature is below 5°C.

INFRA PRIVATE LTD

## Health & Safety

- · Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of contact with skin, rinse with plenty of clean water, then cleanse with soap andwater. Do not use solvent to clean the contacted area.
- In case of contact with eyes, wash immediately with plenty of clean water and seek medicaladvice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

## **Packing**

10 kg pack consists of Component A (Resin) - 3.6 kg, Component B (Hardener) - 0.9 kg and Component C (Aggregate) - 5.5 Kg.

#### **Storage**

Do not allow product to freeze. Store in a dry area at temperatures between 10°C and 35°C in the original unopened containers.

#### **Shelf Life**

12 months in original unopened sealed conditions.







# **Product Range**

Waterproofing and Insulation
 Road Surfacing
 Sealants and Additives
 Pipeline Coating

■ Protective / Anti-Corrosive Coating ■ Epoxy Flooring

■ Grouts / Admixtures ■ RestoFix- Repair / Rehabilitation
■ Other Construction Chemicals

85 Years of Trust

Advisory Cell: +91 81302 81114

220401