

VOPSEA DECOCORK

DATE TEHNICE

CARACTERISTICILE PRODUSULUI	
Densitate (UNE-EN ISO 2811-1)	1,25 g/cm ³
Materii non volatile (1h - 125°) (UNE-EN ISO 3251)	52,00 %
Materii non volatile/volum (UNE-EN ISO 3233-3)	40,20 %
Timp de uscare(UNE 48301) (grosime film: 95 µm)	Uscat la atingere: 30 min. Uscare totală: 1h. 35 min.
Consum (R)	0,25 kg/m ² → 80 µm 0,31 kg/m ² → 100 µm
Consum (R)	5,0 m ² /l → 80 µm 4,0 m ² /l → 100 µm
pH	9±0,5



DECOPROYEC®