



PRODUCT BULLETIN 3200 BRONZE

General Purpose Silicone Sealant

DESCRIPTION

STRONG SEAL 3200 BRONZE General purpose sealant is economic grade single component Acetic cure silicone sealant which vulcanizes on exposure to moisture in the air at room temperature, to produce a flexible elastomeric sealant. It is suitable for all common construction and glazing application. It is easy to apply and offers excellent adhesion to a variety of nonporous substrates such as glass, glazed ceramic tiles and aluminium. It is resistant to ozone, ultra-violet radiation and temperature extremes.

KEY PERFORMANCE PROPERTIES

- ❖ Single component sealant hence easy to use.
- ❖ Cures at room temperature at ambient humidity conditions.
- ❖ All temperature gun ability – can be applied in all temperatures.
- ❖ Excellent resistance to weathering, moisture, ozone, UV, temperature Extremes etc.

TYPICAL PROPERTIES

Colour	White, Clear, Brown, Grey, Beige, Cream & Clear translucent
Consistency	Non-Slump Paste
Cross Linking System	Acetoxy cure
Skin Forming Time	7-8 minutes
Tack Free Time	20 minutes
Specific Gravity	≤0.92
Hardness (Shore A)	8
Depth Cure Rate (mm/Day)	2mm – 2.5 mm
Viscosity Flow	Non Sag
Tooling Time	15 minutes
Tensile Strength	0.60
Elongation %	> 350%
Young Modulus	0.18
Application Temperature Range	- 200C to 1200C
Elastic Recovery, % Approx.	>40
Tear Strength ASTM D 624, Form B	2N/mm ²
Shrinkage DIN 53504 S3A	35%-40%
Shelf life in months from production date	12 Months



APPLICATION AREAS

- Aluminium / Glass and standard glazing
- Curtain wall jointing.
- Plumbing and Sanitary applications
- Metal to metal joints and duct work sealing.
- Draught proofing.
- Sealing door / window's frames, tiling,
- Realizing a flexible joint in assembling sink and decorative parts.
- Sealing works in air conditioning systems.
- Sealing Shop windows and greenhouses.
- All other general purpose sealing applications

Application method: Surface must be clean, dry and should be free from oil, grease, dust and frost. After suitable joint preparation and masking, attach the nozzle to cartridge, cut to required dimension and the sealant is gunned into gap continuously and tooled within 5 minutes. Do not use in totally confined spaces because the sealant requires atmospheric moisture to cure.

Handling and Storage: No special precaution has to be exercised. Always follow appropriate personal and industrial hygiene practices. Avoid direct contact with eyes, skin. Keep out of reach of children. Refer MSDS for further information. Store below 25° Centigrade in a cool dry shaded area.

Note: The information in this data sheet is given in good faith but without warranty, as conditions of storage and use may vary which is beyond our control. User is requested to determine whether the STRONG SEAL products are fit for a particular purpose and suitable for user's method of use and applications.