



Version: 20 July 2017

POTASSIUM GOLD CYANIDE

68.2% AND 68.3%



Conflict Free Gold

In July of 2010, the United States Congress passed legislation requiring those corporations that are required to report to the SEC (United States Securities and Exchange Commission) to annually report the use of „Conflict Materials“ in the manufacture of their products. We have a responsibility to respect human rights and not contribute to conflict. Whilst we are not an SEC reporting company, we see it as our responsibility to act upon this legislation with the aim to enable designation of all Umicore’s gold as „Conflict Free“. At this time, Umicore is not aware of the use of any Conflict Materials in its supply chain and sources no gold from DRC. Umicore is already engaged in a group-wide initiative to ensure sustainable sourcing of all raw materials in its supply chain. We will not tolerate any direct or indirect support to non-state armed groups through the extraction, transport, trade, handling or export of minerals.



Advantages

- Fast soluble in water
- Conventional true value of gold content
- Little impurities
- Does not raise dust
- Thermally stable up to about 200 °C
- Not sensible to light
- Does not decompose in air
- Free flowing

Applications

- For neutral gold electrolytes
- For acidic gold electrolytes
- Connectors
- Costume jewellery
- PCBs
- Semiconductors
- Bathroom fittings
- Writing utensils

POTASSIUM GOLD CYANIDE

68.2% AND 68.3%



TECHNICAL SPECIFICATIONS

The contents of impurities are below the following values:

Ag	0.002 %	= 20 ppm
Cu	0.0001 %	= 1 ppm
Cr	0.0002 %	= 2 ppm
Fe	0.0001 %	= 1 ppm
Na	0.04 %	= 400 ppm
Ni	0.0002 %	= 2 ppm
Pb	0.0003 %	= 3 ppm

Characteristics

Bulk density	approx. 1500 g/l
Solubility in water	20 °C: 140 g/l 80 °C: 1000 g/l

Umicore Galvanotechnik GmbH
Klarenbergstrasse 53-79
73525 Schwaebisch Gmuend (Germany)

Technical Support: Phone +49 7171 607-203
Sales Department: Phone +49 7171 607-204

www.ep.umicore.com


umicore
Electroplating

The information and statements contained herein are based on our experience in the fields of research and applied technology and are believed to be accurate at the time of publication, but - unless agreed in writing - we make no warranty with respect thereto, including but not limited to any results to be obtained. This product information sheet in the English language prevails any translation.